



衢州伯昕科技有限公司
QUZHOU BOXIN TECHNOLOGY CO., LTD.

ADD:No.152,Houwu Vilage, Gouxi Township,Kecheng District,Quzhou City, Zhejiang Province

Contact: David Xu

Tel/WhatsApp: +86 19818000617

Email: david@boxinmaterial.com

PU Wood Painting Formulation (PU木器漆)			
No	Material	Model	Dosage (g)
Main Agent			
1	Alkyd Resin (醇酸树脂)	-	80
2	Xylene(二甲苯)	-	6
3	BAC(丁酯)	-	6.1
4	Matting Powder (消光粉)	524	7
5	Wetting Agent (湿润剂)	BYK103	0.3
6	Leveling Agent (流平剂)	BYK306	0.3
7	Defoamer (消泡剂)	BYK141	0.3
Hardener			
1	TDI adttive hardener (通用固化剂)	CL503V-75	40%
2	Trimer curing hardener (通用固化剂)	CL501M	30%
3	BAC(丁酯)	-	30%
Thinner			
1	BAC(丁酯)	-	20%
2	XL (二甲苯)	-	70%
3	CYC (环己酮)	-	10%
Mixing Ratio: Main Agent : Hardener : Thinner = 1 : 0.5 : 0.9			